



HUBER ENGINEERED MATERIALS



# Hubercarb<sup>®</sup> Q Series Calcium Carbonate Products

QUINCY, IL



# The Hubercarb® Q Series

## Many Products To Satisfy Many Application Needs

Hubercarb® Q Series products include ultra-fine, fine, medium-fine and granular particle size calcium carbonates. Several of these products have been surface-modified to enhance end-use performance.


## Our Key Ingredients: Consistency and Quality Starts At The Beginning

Huber's calcium carbonate mine in Quincy, Illinois, is known for its natural uniformity. It produces stone of consistent purity and brightness. The excellent uniformity of this deposit assures the product we deliver to you years from now will have the same purity and brightness as the product we deliver today. Our processes are certified to ISO standards and when combined with Six Sigma® tools, you are ensured consistent, high performing products time after time.

## Typical Physical Properties — Ultra-Fine and Fine Products

Hubercarb® Q Series	Q2PT	Q2	Q2T	Q3	Q3T	Q4	Q6
Surface Treatment	Treated		Treated		Treated		
Median Particle Size (µ, SediGraph®)	2	2	2	3.2	3.2	4.3	6
Dry Brightness (Hunter Reflectance)	90	90	90	89	88	88	87
Oil Absorption (lbs oil/100 lbs, ASTM D-281)	16	18	16	18	15	17	16
Moisture (% , ASTM D-280)	0.2	0.2	0.2	0.2	0.2	0.2	0.15
Water Demand (ml/100 gms)		68		55		54	45
Loose Bulk Density (lbs/ft³, ASTM C-110)	44	44	41	40	40	40	45
Compacted Bulk Density (lbs/ft³, ASTM C-110)	62	52	55	60	60	60	65
325 Mesh Residue (max, %)	0.005	0.005	0.005	0.005	0.005	0.005	0.01
Hegman Grind (ASTM D-1210)	6	6.5	6.5	6	6	6	5

## Particle Size Distribution — SediGraph® Method



Rigid PVC Pipe is a key Hubercarb® Q Series application.



CALCIUM CARBONATE

## Typical Physical Properties — Medium-Fine and Granular Products

Hubercarb® Q series	Q325	Q200	Q200T	Q100	Q60	Q40-200	Q12-40	Q5-20
Surface Treatment			Treated					
Median Particle Size (μ, LLS-CILAS®)	13	22	22	24	20			
Dry Brightness (Hunter Reflectance)	86	84	84	83	78			
Oil Absorption (lbs oil/100 lbs, ASTM D-281)	14	12	12	12	12			
Moisture (% , ASTM D-280)	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Water Demand (ml/100 gms)	40	36		36				
Loose Bulk Density (lbs/ft <sup>3</sup> , ASTM C-110)	50	55	55	55	55	85	90	88
Compacted Bulk Density (lbs/ft <sup>3</sup> , ASTM C-110)	80	80	80	80	95	98	100	98

## Particle Size (Screen) Analysis

Mesh Size	Q325	Q200	Q200T	Q100	Q60	Q40-200	Q12-40	Q5-20
-4								100
-6								94
-8							100	48
-12							95	9
-16							72	3
-20						100	56	2
-40				100	100	97	7	
-60		100	100	99.9	99.6	60	3	
-100	100	99.9	99.9	99	96.5	23		
-200	99.9	99	99	79	78	6		
-325	99.5	82	82	66	61			

We look forward to providing you with the highest quality products, technical service support and customer care.

# Hubercarb® Q Series Calcium Carbonate Products

## Typical Chemical Analysis

Chemical	Percent
Calcium Carbonate	96.5%
Magnesium Carbonate	2.0%
Silicas and Silicates	1.0%
Other	0.5%

## Other Typical Properties

Color	White
Alkalinity (as NaOH, ASTM D-1208)	0.4 mg/gm
pH (ASTM D-1208)	9.4 (saturated solution)
Hardness (Handbook of Chemistry and Physics)	3 Mohs, relatively non-abrasive
Solubility (Handbook of Chemistry and Physics)	0.0035 gm/100 ml H <sub>2</sub> O at 100°C
Particle Shape (Microscope)	Irregular, uniaxial
Specific Gravity (ASTM D-153)	2.7
Refractive Index (Handbook of Chemistry and Physics)	1.6
Weight/Solid Gallon (s.g. x 8.345)	22.6 lbs/solid gallon (0.0443 solid gallons/pound)
Linear Expansion Coefficient (Handbook of Chemistry and Physics)	4.3 x 10 <sup>-6</sup> /°C

### Q Series Products

- Hubercarb® Q2PT
- Hubercarb® Q2
- Hubercarb® Q2T
- Hubercarb® Q3
- Hubercarb® Q3T
- Hubercarb® Q4
- Hubercarb® Q6
- Hubercarb® Q325
- Hubercarb® Q200
- Hubercarb® Q200T
- Hubercarb® Q100
- Hubercarb® Q60
- Hubercarb® Q40-200
- Hubercarb® Q12-40
- Hubercarb® Q5-20

### Plant Location

Huber Carbonates, LLC  
3150 Gardner Expressway  
Quincy, IL 62305

### Applications

- Paints and Coatings
- Rigid PVC Pipe
- Joint Compound
- Caulks and Sealants
- Adhesives
- Rubber
- Vinyl Flooring
- Polyolefin Film
- Traffic Paint
- Cleansers
- Ceramics
- Drilling Fluids
- Asphalt Products
- Pesticides
- Agriculture
- Concrete Products

### Other Products

- Hubercarb® G Series Calcium Carbonate
- Hubercarb® M Series Calcium Carbonate
- Hubercarb® W Series Calcium Carbonate

### Additional Products Available From

Marble Hill, Georgia  
Marble Falls, Texas



HUBER ENGINEERED MATERIALS

For more information or to order samples, contact us:

**1-866-JMHUBER (1-866-564-8237)**

**[www.hubermaterials.com/cc](http://www.hubermaterials.com/cc)**

**Email: [hubermaterials@huber.com](mailto:hubermaterials@huber.com)**



ISO 9001:2015 Certified  
Quality Management System



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages. Hubercarb® is licensed to Huber Carbonates, LLC and is a trademark of the J.M. Huber Corporation for calcium carbonate in various countries around the world. Six Sigma® is a registered trademark of Motorola. SediGraph® is a registered trademark of Micromeritics Instrument Corporation. CILAS® is a registered trademark of Campagne Industrielle des Lasers Cilas.

©2019 Huber Carbonates, LLC

GCC/Q Series/NA/RevXIII/March2019

QUINCY, IL