



FIRE RETARDANT ADDITIVES



Kemgard 981 Used to Replace Antimony Oxide: Achieves V-0 with Chlorinated FR

Application Bulletin #2310

Polypropylene Formulation
62% resin, 27% Clororez 760, 1% Ba/Cd stabilizer

Flame Retardant	94UL
10% antimony oxide	VO
5% antimony oxide 5% Kemgard 981	VO

J.M. Huber Corporation-Huber Engineered Materials
3100 Cumberland Blvd. Ste. 600 Atlanta, GA 30339
866-564-8237
www.kemgard.com

©2013 J.M. Huber Corporation. Kemgard® is a registered trademark of the J.M. Huber Corporation.

THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages.

P
O
l
y
p
r
o
p
y
l
e
n
e