




FIRE RETARDANT ADDITIVES



Kemgard 911C Increases Oxygen Index: Antimony-Free Cable Jacket Compound

Application Bulletin #2520

Neoprene Rubber



Common Ingredients	
Polychloroprene (Neoprene GW, DuPont)	Titanium Dioxide - 10 phr
High Activity Magnesia - 3 phr	Stearic Acid - 1 phr
Zinc Oxide - 5 phr	Precipitated Whiting - varied*
Aluminum Trihydrate - 65 phr	Flame Retardant -0-20*

*The precipitated whiting was varied to maintain a constant total flame retardant and whiting of 50 phr.

J.M. Huber Corporation-Huber Engineered Materials
3100 Cumberland Blvd. Ste. 600 Atlanta, GA 30339
866-564-8237
www.kemgard.com

©2013 J.M. Huber Corporation. Kemgard® is a registered trademark of the J.M. Huber Corporation.

THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages.