



J.M. Huber Finland Oy
Telakkatie 5
FIN-49460 Hamina Finland

phone: +358 5 749 91
fax: +358 5 749 95 00
e-mail: hubermaterials@huber.com

HN-532 ALUMINA TRIHYDRATE

DESCRIPTION

HN-532 is a halogen-free, very fine particle size ATH product that provides low cost flame retardant and smoke suppression in a variety of applications. The particle size distribution is specifically designed for low viscosity, high filler loading levels, and excellent processing characteristics, up to 200°C.

APPLICATIONS

HN-532 is recommended for spray-up or hand lay-up FRP applications, filament winding, panel production, resin injection, foam materials, add cast polyester and epoxy parts, coatings, adhesives, latex, vinyl and urethane.

PHYSICAL FORM: White powder
GENERIC TYPE: Alumina trihydrate

MORPHOLOGY: Hexagonal Platelets
CAS No.: 21645-51-2

TYPICAL CHEMICAL ANALYSIS

Al(OH) ₃ , %	99.6
SiO ₂ , %	<0.04
Fe ₂ O ₃ , %	<0.02
Na ₂ O (total), %	0.2
Na ₂ O (soluble), %	0.05
Free Moisture (TGA), 105° C, %	0.46

TYPICAL PHYSICAL PROPERTIES

Screen Analysis	
% < 45 micron	99.98
% < 10 micron	72.4
Median Particle Diameter, microns	6
Loss on ignition, 550° C, %	34.5
Surface Area BET (m ² /gm)	5
Specific Gravity (gm/cm ³)	2.42
Bulk Density- packed (gm/lit.)	900
Brightness Ry	96
CIELAB, L*	98
Moh's Hardness	3.0
Electrical Conductivity, μS/cm	<130
Oil Absorption, ml/100gm	28

PACKAGING & STORAGE

25 kg paper bag, 1000 kg pallet

The product should be stored under dry and clean conditions in its original packing. The moisture content may increase if not stored under dry conditions.

©2015 J.M. Huber Corporation. Huber and the Huber logo are registered trademarks of J.M. Huber Corporation.

THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages.

Revised 9/15