



Hubercarb® G35T
CALCIUM CARBONATE

DESCRIPTION

A high purity, ultra-fine ground calcium carbonate produced from a high brightness marble deposit in Georgia for applications that require high brightness or pure tints. The particles are processed with a proprietary fatty acid based surface treatment which allow the material to be used as an extender in pipe, conduit, rubber, plastics and PVC compounds.

Cumberland Center II
3100 Cumberland Blvd
Suite 600
Atlanta, GA 30339
phone: (678) 247-7300
fax: (678) 247-2797
e-mail: hubermaterials@huber.com
www.hubermaterials.com

TYPICAL PHYSICAL PROPERTIES

Median Particle Size (Cilas®, μ)
Brightness (Hunter reflectance)
Oil Absorption (lbs oil / 100lbs, ASTM D281)
Moisture (% , ASTM D280)
Loose Bulk Density (lb/ft³, ASTM C110)
Compacted Bulk Density (lb/ft³, ASTM C110)
Acid Solubility (% in HCl)
Hegman Grind

G35T

3.2
95
16
0.2
52
63
95 - 98.5
6

PARTICLE SIZE (SCREEN) ANALYSIS

Mesh size
+325 (45μm)

%

0.005

TYPICAL CHEMICAL ANALYSIS

Calcium Carbonate
Magnesium Carbonate
Silica and Silicates
Other

%

96.0
2.5
0.4
1.5

MINERAL PROPERTIES

Color
Alkalinity (as NaOH, ASTM D1208)
pH (ASTM D1208)
Hardness (Hand. Of Chem. & Phy)
Solubility (Hand. Of Chem. & Phy)
Particle Shape (Microscope)
Specific Gravity (ASTM D153)
Refractive Index (Hand. Of Chem. & Phy)
Weight per Gallon (s.g. x 8.345)
Linear Expansion Coefficient (Hand. Of Chem. & Phy)

Marble Hill, Georgia
White
0.4 mg/gm
9.4 (saturated solution)
3 Mohs, relatively non-abrasive
0.0035 gm/100 mL H₂O at 100°C
Irregular, uniaxial
2.7
1.6
22.6 lbs/solid gallon
4.3 x 10⁻⁶/°C

THERE ARE NO IMPLIED WARRANTIES OF MERHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages. Hubercarb® is a registered trademark of J.M. Huber Corporation for calcium carbonate.