



Hubercarb® M3T
CALCIUM CARBONATE

Cumberland Center II
3100 Cumberland Blvd
Suite 600
Atlanta, GA 30339
phone: (678) 247-7300
fax: (678) 247-2797
e-mail: hubermaterials@huber.com
www.hubermaterials.com

DESCRIPTION

An fine ground calcium carbonate produced from a uniform, high calcium limestone deposit in Marble Falls, Texas. The particles are processed with a proprietary fatty acid based surface treatment which allow the material to be used as an extender in pipe, conduit, rubber, plastics and PVC compounds.

TYPICAL PHYSICAL PROPERTIES

	<u>M3T</u>
Median Particle Size (Sedigraph®, μ)	3.3
Brightness (Hunter reflectance)	87
Oil Absorption (lbs oil/ 100 lbs, ASTM D281)	15
Moisture (% , ASTM D280)	0.2
Loose Bulk Density (lb/ft ³ , ASTM C110)	40
Compacted Bulk Density (lb/ft ³ , ASTM C110)	60
Acid Solubility (% in HCl)	92
Hegman Grind (ASTM D1210)	6.5

PARTICLE SIZE (SCREEN) ANALYSIS

	<u>%</u>
Mesh size	
+325 (45μm)	0.01

TYPICAL CHEMICAL ANALYSIS

	<u>%</u>
Calcium Carbonate	92.0
Magnesium Carbonate	1.5
Silica and Silicates	4.5
Other	2.0

MINERAL PROPERTIES

Color	Marble Falls, Texas
Alkalinity (as NaOH, ASTM D1208)	White
pH (ASTM D1208)	0.4 mg/gm
Hardness (Hand. Of Chem. & Phy)	9.4 (saturated solution)
Solubility (Hand. Of Chem. & Phy)	3 Mohs, relatively non-abrasive
Particle Shape (Microscope)	0.0035 gm/100 mL H ₂ O at 100°C
Specific Gravity (ASTM D153)	Irregular, uniaxial
Refractive Index (Hand. Of Chem. & Phy)	2.7
Weight per Gallon (s.g. x 8.345)	1.6
Linear Expansion Coefficient (Hand. Of Chem. & Phy)	22.6 lbs/solid gallon
	4.3 x 10 ⁻⁶ /°C

THERE ARE NO IMPLIED WARRANTIES OF MERHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Huber's Standard Conditions of Sale for the only express warranties applicable to the Huber products. Products incorporating Huber products are not warranted by Huber. In no event is Huber liable for consequential damages. Hubercarb® is a registered trademark of J.M. Huber Corporation for calcium carbonate.