



MARTOXID[®] KMS-94

Einsatzbeispiele / Applications

Fertigverpreßbare Masse zur uniaxialen und isostatischen Verarbeitung; für die Herstellung von oxidkeramischen Erzeugnissen, wie z.B. Mahlmedien, Isolatoren und verschleißfeste Teile.

Feedstock ready to press for uniaxial and isostatic pressing for the production of oxide ceramic bodies such as grinding media, insulating and wear-resistant parts, etc.

Durchschnittsanalyse / Typical analysis

Al ₂ O ₃	[%]	≈ 94.0
Na ₂ O	[%]	≤ 0.1
CaO	[%]	≈ 0.3
Fe ₂ O ₃	[%]	≤ 0.1
SiO ₂	[%]	≈ 4
MgO	[%]	≈ 1
Glühverlust / Loss on Ignition	[%]	≈ 3.0
Schüttdichte / Bulk Density	[kg/m ³]	≈ 1200
Feuchte / Moisture	[%]	≤ 0.35
mittlerer Granulatdurchmesser / median granule size (Siebung / Screening)	[µm]	≈ 100
Typische Verarbeitungseigenschaften / Typical Processing Features:		
Pressdichte / Green Density	(100MPa) [g/cm ³]	≈ 2.4
Sinterdichte / Fired Density	(1600 °C, 2h) [g/cm ³]	≈ 3.7

Shipping Information

Transportation classification: not regulated for transportation
Harmonized tariff number: 28182000

Packaging and minimum order quantity information is available from sales or customer service.

Safety and Handling Information

For specific safety, toxicity and handling information, please refer to the material safety data sheet on this product.

Chemical Registration Numbers

Chem. Bezeichnung / Chem. name: Aluminiumoxid
Formel / formula: Al_2O_3
CAS No.: 1344-28-1
EC/EINECS No.: 215-691-6
UN-Nr.: ---

EUROPE, MIDDLE EAST, AFRICA

Martinswerk GmbH
Kölnener Straße 110
D-50127 Bergheim

Phone: +49-2271-902-0
Fax: +49-2271-902-710

AMERICAS

Huber Engineered Materials
3100 Cumberland Boulevard
Suite 600
Atlanta, Georgia 30339

Phone: +1 (678) 247-7300
Fax: +1 (678) 247-2797

ASIA PACIFIC

Huber Engineered Materials
Zhang Ge Zhuang
Huangdao Sub-district
Qingdao, Shangdon
266555 China

Web: www.martinswerk.de
www.hubermaterials.com

Email: info@martinswerk.com
hubermaterials@huber.com



THERE ARE NO IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Refer to Martinswerk's Standard Conditions of Sale for the only express warranties applicable to the Martinswerk products. Products incorporating Martinswerk products are not warranted by Martinswerk. In no event is Martinswerk liable for consequential damages. **MARTOXID®** is used, applied for, or registered as a trademark of Martinswerk GmbH in various countries around the world.
© April 2016 Martinswerk GmbH